

多层复合产品技术参数表 Heterogeneous Technical information

KARMEEN[®]
INTERNATIONAL 卡曼国际

Description 规格	Standard 标准	Result结果
Total thickness 总厚度	EN 428	2.0 mm
Wear layer thickness 耐磨层	EN 429	0.35mm
Width 宽度	EN 426	2 m
Length of sheet 卷长	EN 426	20 m

CLASSIFICATION 类别

Fire rating 防火等级	GB 8624-2012	B1
Toxic testing 有害物质检测	GB 18586-2001	Good 合格
Electrical resistance 抗电阻性	EN 1081	>10 ⁹⁻¹⁰
Slip resistance dry 防干滑性	EN 13893	≥0.3
Slip resistance wet 防湿滑性	EN 51 130	R9

PERFORMANCES 性能

Castor chair test 轮压测试	EN 425	No damage 合格
Colour fastness 颜色稳定性	EN ISO 105 - B02	≥6
Chemical products resistance 抗化学性	EN 423	Good 好
Dimensional stability 尺寸稳定性	EN 434	≤0.40%
Curl resultant to heat 加热翘曲	EN 434	≤4 mm
Sound reduction 消音率	EN ISO 717/2	Approx. 4 dB
Residual indentation 残余凹陷度	EN 433	Approx. 0.04 mm ≈ 0.04 mm
Anti-bacterial and fungicidal 抗菌防霉性能		Good 好
VOC 挥发物排放量		<10
Surface treatment 表面处理		PUR

INSTALLATION 安装

应按照当地标准进行安装。铺设地板前，应确保地面平滑、坚硬、清洁和干燥。如有需要，应在地面上铺设一层有效的防潮薄膜。安装地板前，应提前24小时将地板材料放置在18-24℃室温内适应环境。

Installation should be carried out in accordance with local standards. Subfloor to be smooth, hard, clean and dry prior to laying. Where applicable the subfloor must incorporate an effective Damp Proof Membrane. The material must be allowed to acclimatize 24 hours before installation in a room temperature of between 18-24 °C.

MAINTENANCE 维护

需使用乳液清洁。定期进行维护以使其保持外观整洁和耐用性。定期清扫和使用中性清洁剂湿擦来维护地板。或者使用具有精细喷雾垫的清洗机进行大面积地面的清洗。

An emulsion dressing is required. Maintenance should be carried out regularly to retain the appearance and durability of the floor. The floorcovering should be maintained with regular sweeping and damp mopping using a neutral cleanser, more intense cleaning should be carried out using a fine spray cleaning pad under a floor machine, or for larger areas combined machine cleaning.

产品结构 PRODUCT STRUCTURE

